

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**



4  
The  
Patent  
Office

PCT/GB 00/0042



INVESTOR IN PEOPLE

GB00/402

09/890413  
The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

REC'D 1 / MAR 2000	
WIPO	PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.


In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

**PRIORITY  
DOCUMENT**

SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)

Signed *Andrew Gentry*  
Dated 23 February 2000



**THIS PAGE BLANK (USPTO)**

# Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

12 FEB 1999

The Patent Office

Cardiff Road  
Newport  
Gwent NP9 1RH

1. Your reference TD/300/4576F/JAK

2. Patent application number  
(The Patent Office will fill in this part)

9903056.1

3. Full name, address and postcode of the or of each applicant (underline all surnames)

PILKINGTON PLC  
PRESCOT ROAD  
ST HELENS  
MERSEYSIDE  
WA10 3TT

Patents ADP number (if you know it)

0444091001

If the applicant is a corporate body, give the country/state of its incorporation

ENGLAND

660449001

4. Title of the invention

IMPROVEMENTS IN COATING GLASS

5. Name of your agent (if you have one)

ANTHONY CHARLES HALLIWELL

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

GROUP PATENTS DEPARTMENT  
PILKINGTON TECHNOLOGY CENTRE  
PILKINGTON PLC  
HALL LANE, LATHOM,  
ORMSKIRK  
LANCASHIRE L40 5UF

Patents ADP number (if you know it)

0626497001

6152343001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country	Priority application number (if you know it)	Date of filing (day / month / year)
-	-	-

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application	Date of filing (day / month / year)
-	-

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

- a) any applicant named in part 3 is not an inventor, or
  - b) there is an inventor who is not named as an applicant, or
  - c) any named applicant is a corporate body.
- See note (d))

Yes

# Patents Form 1/77

9. Enter the number of sheets for each of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form	-
Description	9
Claim(s)	4
Abstract	1
Drawing(s)	-

10. If you are also filing any of the following, state how many against each item.

Priority documents	-
Translations of priority documents	-
Statement of inventorship and right to grant of a patent (Patents Form 7/77)	-
Request for preliminary examination and search (Patents Form 9/77)	1
Request for substantive examination (Patents Form 10/77)	-
Any other documents (please specify)	-

11. I/~~we~~ request the grant of a patent on the basis of this application.

Signature

*Anthony C. Halliwell*

Date 11 Feb 99.

Anthony Charles Halliwell (Agent for the Applicant)

12. Name and daytime telephone number of person to contact in the United Kingdom Mr J A Knowles - 01695 54391

## Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

## Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

# Improvements in Coating Glass

This invention relates to a process for the production of a coated substrate and, in particular, it relates to a process for the production of a coated substrate comprising depositing a reflective metal layer on to a substrate by a low pressure deposition process.

Substrates coated with a reflective metal layer, typically silver 5 nm to 30 nm thick, may be produced with low emissivity and a high visible light transmission i.e. reflecting a high proportion of infra-red radiation incident upon them but allowing visible radiation to pass through. For optimum light transmission the silver layers are sandwiched between anti-reflection layers usually of metal oxide. The use of such coatings on window glass leads to a reduction in heat loss. Substrates having such coatings are described, for example, in UK patent specification GB 2 129 831.

Coatings having multiple (usually two) silver layers, each silver layer being sandwiched between anti-reflection layers, may also be produced. Coatings with multiple silver layers have both low emissivity, and with appropriate layer thicknesses, a low transmission of solar heat.

Coatings with silver layers are produced by deposition processes in a coating atmosphere at low pressure, especially by sequential deposition of a metal oxide anti-reflection layer, a silver layer, and a metal oxide anti-reflection layer. The metal oxide layers are usually deposited by reactive sputtering in a coating atmosphere containing oxygen and an inert gas (usually argon). Silver and other reflective metal layers are deposited by sputtering in an inert gas (usually argon). In US patent specification 5,837,361 a process for the production of a coating having layers of bismuth oxide ( $\text{Bi}_2\text{O}_3$ ), zinc oxide, silver, nichrome, tin oxide and bismuth oxide is described, the metal oxide layers being reactively sputtered in

an argon atmosphere containing oxygen and the silver layer being sputtered in an argon atmosphere with the addition of 5% by volume hydrogen.

In commercial production of sputtered coatings, sputtering of each layer usually proceeds in a sputtering chamber that has been initially evacuated to high vacuum (usually of about  $10^{-6}$  mbar) and then raised to an operating pressure of around  $10^{-3}$  mbar by flowing the gases making up the coating atmosphere into the chamber. The operating pressure is low so that the path length of the coating species sputtered from the target is high enough to reduce scattering and thereby maintain the efficiency of the coating process. Deposition of coatings may be performed in a single chamber having a readily changeable atmosphere or multiple, serially connected deposition chambers each containing the desired atmosphere. In the multiple chamber case, the substrate is moved sequentially between the chambers, which are separated by gas-tight slit valves to alleviate leakage of the coating atmosphere between chambers. It is particularly important to alleviate leakage of oxygen from the metal oxide deposition chambers to the silver deposition chambers because the reflective metal layer oxidises or degrades if deposited in a coating atmosphere containing oxygen. To reduce leakage further there are usually additional chambers, positioned between the deposition chambers, which are pumped at high rates so that oxygen in the coating atmospheres used for sputtering metal oxide layers is removed before it can leak into the silver deposition chamber.

The need for high pumping rates in the deposition chambers and in the additional chambers requires expensively high pumping capacity, slows production rates considerably and leakage can still occur. Particular problems arise where the substrate to be coated is curved. In order to accommodate the greater cross-section of curved substrates, high clearance slit valves are required with an increased likelihood of leakage and in consequence a need for even higher pumping rates.

We have discovered that a low pressure deposition process for depositing a reflective metal layer can tolerate the presence of oxygen if a gaseous oxygen scavenger is present in the coating atmosphere.

The present invention accordingly provides a process for the production of a coated substrate comprising depositing a reflective metal layer on to a substrate by a low pressure deposition process performed in a first coating atmosphere, characterised in that the first coating atmosphere contains a gaseous oxygen scavenger, wherein when the reflective metal layer is deposited as a layer in a multilayer coating which also contains a bismuth oxide layer said gaseous oxygen scavenger is not hydrogen.

Oxygen can be present at a level that is too low to conveniently measure but nevertheless is high enough to oxidise or degrade the reflective metal layer. Thus, the first coating atmosphere may contain the oxygen scavenger as a preventative measure, even if the deposition process is performed in a first coating atmosphere that contains no measurable amount of oxygen.

Usually, the deposition process is performed in a first coating atmosphere that contains oxygen. The presence of oxygen in the first coating atmosphere may arise by leakage from a deposition chamber containing a second coating atmosphere that contains oxygen or from outside (e.g. from the air).

The gaseous oxygen scavenger may be any substance capable of combining chemically with oxygen under the conditions of the low pressure deposition process. Such combination may take place in the gas phase or on the surface of the substrate.

Preferably each molecule of the oxygen scavenger is capable of combining with more than one molecule of oxygen. This is advantageous because then only a small amount of oxygen scavenger need be added to the first coating atmosphere. Adding a large amount of oxygen scavenger to the atmosphere may increase the pressure and therefore reduce the

efficiency of deposition. Preferably the gaseous oxygen scavenger has a relatively high vapour pressure at room temperature.

It is advantageous if the gaseous oxygen scavenger is such that the products of its interaction with the surface of the reflective metal layer or of its combination with oxygen are themselves gaseous because the likelihood of solids contamination of the reflective metal layer is thereby reduced. A preferred oxygen scavenger is a hydrocarbon (for example an alkane, alkene, or alkyne), more preferably a  $C_1$  to  $C_4$  hydrocarbon (for example ethane, ethylene, acetylene, propane or butane) and most preferably methane. Oxygen scavengers that are less preferred but may also be suitable include hydrogen, carbon monoxide, nitric oxide and organic compounds, for example, methanol, ethanol or formaldehyde.

Preferably, the reflective metal layer is deposited in a first coating atmosphere comprising a flowing gaseous mixture and wherein the gaseous oxygen scavenger is introduced into the first coating atmosphere by incorporation in the flowing gaseous mixture.

The gaseous oxygen scavenger may also or alternatively be introduced into the first coating atmosphere by incorporating it into a second coating atmosphere of e.g. a second deposition chamber so that at least some of it can leak from that second coating atmosphere into the first.

The amount of oxygen scavenger in the first coating atmosphere should not be so great as to unacceptably increase the pressure, but should be sufficient to alleviate oxidation or degradation of the reflective metal layer. In practice, if the quality of the reflective metal coating deteriorates during deposition (the deterioration is determined, for example, by an increase in sheet resistance), the amount of oxygen scavenger in the first coating atmosphere would be increased to reverse, alleviate or prevent the deterioration.

Thus, preferably, the first coating atmosphere contains the gaseous oxygen scavenger in an amount that is sufficient to alleviate oxidation and/or degradation of the reflective metal layer.

Usually the first coating atmosphere contains the gaseous oxygen scavenger in an amount that exceeds 15 mol% of the amount of oxygen, preferably that exceeds 30 mol% of the amount of oxygen, and more preferably that exceeds 50 mol%, of the amount of oxygen.

In a preferred embodiment, the process additionally comprises depositing a metal oxide anti-reflection layer by a low pressure deposition process, performed in a second coating atmosphere that contains oxygen, before depositing the reflective metal layer. Usually, at least one additional metal oxide anti-reflection layer will be deposited so that the reflective metal layer is sandwiched between metal oxide anti-reflection layers. When two or more reflective metal layers are deposited (e.g. to provide a coating with low solar heat transmission) each reflective metal layer will usually be sandwiched between metal oxide anti-reflection layers. Examples of metal oxides suitable for use as anti-reflection layers include: zinc oxide, tin oxide, silicon oxide, zirconium oxide, titanium oxide, niobium oxide, molybdenum oxide, tungsten oxide, silicon nitride, silicon oxynitride and silicon oxycarbide. Additional layers of metal oxide, metals (e.g. nichrome, inconel or titanium) or other materials may also be present in the multi-layer coating by, for example, being deposited between the metal oxide anti-reflection layers and the reflective metal layers and/or between the substrate and a metal oxide layer.

Preferably, the reflective metal layer is a silver layer, and preferably the reflective metal layer has a thickness in the range 5 to 30 nm, more preferably in the range 7 to 18 nm. At thicknesses lower than about 5 nm the reflective metal layer may be discontinuous (this results from the growth mechanism of a layer and may occur even on a flat substrate) and will then not possess the properties of the bulk metal resulting in poor infra red reflecting

properties. Thicknesses higher than about 30 nm may cause the coated glass to have too high a visible light reflectivity.

It is known to estimate the infra red reflection of reflective metal layers by measuring the sheet resistance of the coating. A high sheet resistance indicates poor infra red reflecting properties (i.e. high emissivity), whereas a low sheet resistance indicates good infra red reflecting properties (i.e. low emissivity). Oxidation or oxygen induced degradation of a reflective metal layer increases the sheet resistance with consequently poorer infra red reflecting properties. The sheet resistance of a layer is defined as:

$$R_s = \rho / d$$

where  $\rho$  is the resistivity of the layer, and  $d$  is its physical thickness (see, for example, *Thin Film Technology*, R.W. Berry, P.M. Hall and M.T. Harris (D. Van Nostrand, 1968) pp 329-331). The units of sheet resistance are  $\Omega$  / square.

In the present invention, preferably the sheet resistance of the reflective metal layer is below 12  $\Omega$  / square. It is advantageous if the sheet resistance of the reflective metal layer deposited in a first coating atmosphere containing oxygen is below 12  $\Omega$ /square, preferably below about 8  $\Omega$ /square.

Low pressure deposition processes are performed in flowing gas at pressures of below about  $10^{-1}$  mbar, or preferably lower and include such processes as sputtering, reactive sputtering, evaporation and other forms of physical vapour deposition. The preferred low pressure deposition process for depositing the reflective metal layer is sputtering.

In prior art processes, deposition of each layer usually proceeds in a sputtering chamber, which has been initially evacuated to about  $10^{-6}$  mbar to ensure removal of air, especially oxygen. The pressure of the chamber is then raised to an operating pressure of approximately  $10^{-3}$  mbar by injection of the gases making up the coating atmosphere (usually argon for

sputtering of the reflective metal and a mixture of argon and oxygen for sputtering of metal oxides).

The present invention is of particular benefit because with a gaseous oxygen scavenger present in the first coating atmosphere, the deposition process is better able to tolerate incomplete removal of air.

Thus, in one embodiment, the present invention additionally provides a low pressure process for the deposition of a reflective metal layer on a substrate, performed in a deposition chamber containing a coating atmosphere, comprising evacuating the deposition chamber to a low first pressure, introducing a coating gas into the deposition chamber thereby raising the pressure therein to a higher second pressure of about  $10^{-3}$  mbar, and sputtering the reflective metal layer at the second pressure, characterised in that the first pressure is about  $10^{-4}$  mbar and in that the coating atmosphere contains a gaseous oxygen scavenger.

This is advantageous because evacuating to a higher pressure is more easily, rapidly and cheaply achieved (particularly because a lower pumping capacity is required).

The substrate to be coated is preferably glass but may be, for example, a transparent plastics substrate. The substrate may be flat or curved.

Coated glass produced by a process according to the invention has uses in many areas of glass use including in multiple glazing units and in laminated glass.

The invention is illustrated by the following Examples in which silver reflective metal layers were deposited on glass substrates by sputtering in a coating atmosphere containing argon, oxygen to simulate oxygen leakage and methane as oxygen scavenger.

#### Examples 1-5

Layers of silver were deposited on soda-lime glass substrates (of dimension 20 x 20 cm, 20 x 10 cm or 20 x 40 cm) at room temperature and at a pressure of  $2 \times 10^{-3}$  mbar by DC magnetron sputtering using a silver target of 99.9% purity and a power density (over

approximately  $160 \text{ cm}^2$ ) of about  $3.1 \text{ W/cm}^2$ . The coating atmosphere consisted of argon, oxygen and methane. All gases were obtained from B.O.C. Ltd and were Zero grade.

The glass substrates were positioned vertically in a holder and advanced at a glass traversal speed of 10-35 cm/min through the sputtering zone with a coating aperture of dimension approximately 1 cm.

After coating, the thickness of the silver layer was measured by computer fitting the optical transmission and reflection spectra of the coated glass, the spectra having been determined using a Hitachi U400 spectrophotometer.

The sheet resistance (in ohm/square) of the silver coatings was determined by a non-contact conductance monitor (Delcon Instruments 717 Conductance monitor).

Table 1 describes, for Examples 1-5, the flow rates of the gases in the coating atmosphere (in standard  $\text{cm}^3$  per minute), the glass traversal speed, the thickness of the silver layer as determined and the sheet resistance of the coated glass.

#### Comparative Examples A and B

Comparative Example A was conducted under the same conditions as Example 1 except that no oxygen and no methane were present in the coating atmosphere.

Comparative Example B was also conducted under the same conditions as Example 1 except that no methane was present in the coating atmosphere.

Table 2 describes, for Comparative Examples A and B, the flow rates of the gases in the coating atmosphere, (in standard  $\text{cm}^3/\text{min}$ ), the glass traversal speed, the thickness of the silver layer and the sheet resistance of the coated glass.

Table 1

Example	Flow rates of gases (standard cm <sup>3</sup> /min)			Glass traversal speed (cm/min)	Thickness of silver layer (nm)	Sheet resistance (Ω/square)
	Ar	O <sub>2</sub>	CH <sub>4</sub>			
1	22	4	6	35	7.3	8.1
2	22	4	6	25	11.6	5.3
3	22	4	0.6	35	9.2	12.0
4	22	40	20	20	8.7	11.9
5	22	40	30	10	15	3.8

Table 2

Comparative Example	Flow rates of gases (standard cm <sup>3</sup> /min)			Glass traversal speed (cm/min)	Thickness of silver layer (nm)	Sheet resistance (Ω/square)
	Ar	O <sub>2</sub>	CH <sub>4</sub>			
A	22	-	-	35	9.2	5.0
B	22	4	-	35	9.2	12.5

Claims

1. A process for the production of a coated substrate comprising depositing a reflective metal layer on to a substrate by a low pressure deposition process performed in a first coating atmosphere, characterised in that the first coating atmosphere contains a gaseous oxygen scavenger, wherein when the reflective metal layer is deposited as a layer in a multilayer coating which also contains a bismuth oxide layer said gaseous oxygen scavenger is not hydrogen.
2. A process as claimed in claim 1 wherein the deposition process is performed in a first coating atmosphere that contains no measurable amount of oxygen.
3. A process as claimed in claim 1 wherein the deposition process is performed in a first coating atmosphere that contains oxygen.
4. A process as claimed in any of the preceding claims wherein the gaseous oxygen scavenger is a hydrocarbon.
5. A process as claimed in claim 4 wherein the gaseous oxygen scavenger is a C<sub>1</sub> to C<sub>4</sub> hydrocarbon.
6. A process as claimed in claim 5 wherein the gaseous oxygen scavenger is methane.
7. A process as claimed in any one of the preceding claims wherein the gaseous oxygen or scavenger is hydrogen, carbon monoxide, nitric oxide, methanol or ethanol.

8. A process as claimed in any one of the preceding claims wherein the reflective metal layer is deposited in a first coating atmosphere comprising a flowing gaseous mixture and wherein the gaseous oxygen scavenger is introduced into the first coating atmosphere by incorporation in the flowing gaseous mixture.
9. A process as claimed in any one of the preceding claims wherein the first coating atmosphere contains the gaseous oxygen scavenger in an amount that is sufficient to alleviate oxidation and/or degradation of the reflective metal layer.
10. A process as claimed in any of claims 3 to 9 wherein the first coating atmosphere contains the gaseous oxygen scavenger in an amount that exceeds 15 mol% of the amount of oxygen.
11. A process as claimed in any of claims 3 to 10 wherein the first coating atmosphere contains the gaseous oxygen scavenger in an amount that exceeds 30 mol% of the amount of oxygen.
12. A process as claimed in any of claims 3 to 11 wherein the first coating atmosphere contains the gaseous oxygen scavenger in an amount that exceeds 50 mol% of the amount of oxygen.
13. A process as claimed in any one of the preceding claims that additionally comprises depositing a metal oxide anti-reflection layer by a low pressure deposition process,

performed in a second coating atmosphere that contains oxygen, before depositing the reflective metal layer.

14. A process as claimed in any one of the preceding claims wherein the reflective metal layer is a silver layer.
15. A process as claimed in any one of the preceding claims wherein the reflective metal layer has a thickness in the range 5 to 30 nm.
16. A process as claimed in claim 15 wherein the reflective metal layer has a thickness in the range 7 to 18 nm.
17. A process as claimed in any one of the preceding claims wherein the sheet resistance of the reflective metal layer is below  $12 \Omega / \text{square}$ .
18. A process as claimed in any one of claims 3 to 17 wherein the sheet resistance of the reflective metal layer deposited in a first coating atmosphere that contains oxygen is below  $12 \Omega / \text{square}$ .
19. A process as claimed in any one of claims 3 to 18 wherein the sheet resistance of the reflective metal layer deposited in a first coating atmosphere that contains oxygen is below  $8 \Omega / \text{square}$ .

20. A process as claimed in any one of the preceding claims wherein the low pressure deposition process for depositing the reflective metal layer is sputtering.
21. A low pressure process for the deposition of a reflective metal layer on a substrate, performed in a deposition chamber containing a coating atmosphere, comprising evacuating the deposition chamber to a low first pressure, introducing a coating gas into the deposition chamber thereby raising the pressure therein to a higher second pressure of about  $10^{-3}$  mbar, and sputtering the reflective metal layer at the second pressure, characterised in that the first pressure is about  $10^{-4}$  mbar and in that the coating atmosphere contains a gaseous oxygen scavenger.
22. A process as claimed in any one of the preceding claims wherein the substrate is curved.
23. A coated glass produced by a process as claimed in any one of the preceding claims.
24. A process as claimed in claim 1 substantially as hereinbefore described with particular reference to Examples 1-5.

## ABSTRACT

### Improvements in Coating Glass

A process for the production of a low emissivity coated glass comprising depositing a reflective metal, especially a silver, layer by a low pressure deposition process performed in a coating atmosphere that contains a gaseous oxygen scavenger. The presence of the gaseous oxygen scavenger alleviates oxidation of the silver layer by any oxygen gas present in the coating atmosphere. The gaseous oxygen scavenger may be a hydrocarbon and is preferably methane. The coating process is preferably sputtering.

**THIS PAGE BLANK (USPTO)**

PCT/SB00/00402

10/2/00CP

Plikington PLC